

United States Patent [19]

Reisch

[11] Patent Number: 4,985,491

[45] Date of Patent: Jan. 15, 1991

[54] **POLYURETHANE SEALANTS MADE USING
HIGH MOLECULAR WEIGHT POLYOLS
PREPARED WITH DOUBLE METAL
CYANIDE CATALYSTS**

[75] Inventor: John W. Reisch, Guilford, Conn.

[73] Assignee: Olin Corporation, Cheshire, Conn.

[21] Appl. No.: 417,356

[22] Filed: Oct. 5, 1989

[51] Int. Cl.⁵ C08L 75/04

[52] U.S. Cl. 524/875; 528/59;
528/60; 528/61; 528/64; 528/65

[58] Field of Search 524/875; 528/59, 60,
528/61, 64, 65

[56] **References Cited**

U.S. PATENT DOCUMENTS

3,829,505 8/1974 Herold 260/611 B
3,941,849 3/1976 Herold 260/607
4,335,188 6/1982 Igi et al. 428/458

4,355,188 10/1982 Herold et al. 568/620
4,472,560 9/1984 Kuyper et al. 526/120
4,477,589 10/1984 van der Hulst et al. 502/169

Primary Examiner—Maurice J. Welsh

Attorney, Agent, or Firm—Dale Lynn Carlson

[57] **ABSTRACT**

This invention relates to a method of fabricating a polyurethane sealant composition employing a polyether triol having a molecular weight of between about 5,000 and about 30,000 and having a level of end group unsaturation of no greater than 0.04 milliequivalents per gram of triol, wherein the triol is fabricated in the presence of a double metal cyanide catalyst. The triol is reacted, alone or in admixture with a diol, with a polyisocyanate to produce an isocyanate-terminated prepolymer. The prepolymer is then chain-extended to produce the desired sealant.

12 Claims, No Drawings